



# PRODUCT SPECIFICATION

# **MXBON® 302**

## Cyanoacrylate Adhesive (Low Blooming, Low Odour type)

### **Description:**

MXBON® 302 is a low blooming and low odour type cyanoacrylate adhesive. The whitening phenomenon of the bonding area is eliminated. MXBON® 302 can be used for bonding a variety of metals, plastics, etc. in specialist applications that require no blooming.

### **Physical Properties:**

Liquid State		Cured State	
Base	Ethoxyethyl Cyanoacrylate	Colour	Yellowish clear
Colour	Clear	Specific Gravity (20°C)	1.17
Specific Gravity (20°)	1.069	Working Temp (°C)	-55°C - 65°C
Refraction Index (nD <sup>20</sup> )	1.439	Refractive Index (nD <sup>20</sup> )	1.48
Flash Point (°C)	>80°C	Dielectric Constant (at 10MHz)	3.5
Shelf Life	6 Months	Dielectric Loss (at 10MHz)	0.067
Boiling Point (°C)	>200°C	Soluble in Acetone, Dimethyl formamide, Nitromethane, Dimethyl sulfoxide	
Viscosity (cP)	40-80		

#### **Bond Strength:**

(TENSILE STRENGTH, CURED FOR 24 HOURS AT 20-25°)

Substrate	KG/CM <sup>2</sup>	Substrate	KG/CM <sup>2</sup>
Rigid PVC to Rigid PVC	25-35	SBR to SBR	5-10
ABS to ABS	50-70	Steel to Steel	140-180
Polycarbonate to Polycarbonate	80-120	Stainless Steel to Stainless Steel	70-100
Polystyrene to Polystyrene	80-100	Aluminum to Aluminum	70-100
Natural Rubber to Natural Rubber	5-9	Copper to Copper	20-35
Neoprene to Neoprene	5-9	Steel to Rigid PVC	5-10
NBR to NBR	5-9	Stainless to Neoprene	5-10
ABS to SBR	5-10		

## **Cure Speed:**

Substrate	Seconds	Substrate	Seconds
ABS to ABS	50-60	NBR to NBR	20-30
Wood to Wood	>60	Stainless steel to Stainless steel	>60
ABS to Stainless steel	45-55	ABS to NBR	25-35
NBR to Stainless steel	45-55	Wood to ABS	>60

Revision date: 01/2025 - Revision: 08





#### PRODUCT SPECIFICATION

# **MXBON® 302**

Cyanoacrylate Adhesive (Low Blooming, Low Odour type)

#### **Directions For Use:**

- 1. Make sure the surfaces to be bonded are clean and dry (preferable to solvent-wipe plastics, glass, rubber and to acid-treat metals).
- 2. Dispense a drop or drops to one surface only. Apply only enough to leave a thin film after compression.
- Press parts together and hold firmly for a few seconds. Good contact is essential. An adequate bond develops in less than one minute. (Maximum strength is achieved in 24 to 48 hours).
- 4. Wipe off excess adhesive from the top of the container and recap MXBON® 302 if left uncapped, may deteriorate by contamination from moisture in the air.
- 5. Because MXBON® 302 polymerises on contact with moisture surfaces, sometimes whitening will occur on the surface of the container or the bonded materials. Should this happen, wipe surfaces well with debonder.

#### Handling & Storage

Storage: Keep products in the unopened container in a cool dry location. The product is best when stored at 2 to 8°C. temperatures less than 2°C can adversely affect product properties. Do not freeze. Keep container tightly closed until ready for use.

Handling: Material removed from containers may be contaminated during use. Do not pour back any product to the original Container. Misuse of product will void all warranties.

#### Precaution

- 1. Use with proper ventilation. Avoid contact with skin and eyes.
- If contact with skin occurs, rinse with warm water or dissolve with appropriate debonder. Do not try to remove forcibly.
- If adhesive gets into your eye, keep eye open and rinse thoroughly. Seek medical attention immediately.
- Keep well out of reach of children.
- 5. Keep adhesive in a cool dry place 20-25°C. For long term storage, refrigeration (5°C) is recommended.

#### Disclaimer:

The data contained herein are furnished for informational purposes only and are believed to be reliable. However, Cartell UK Ltd does not assume responsibility for any results obtained by persons who methods Cartell UK Ltd has no control. It is the responsibility to determine the suitability of Cartell UK's products or any production methods mentioned herein for a particular purpose, and to adopt such precautions as may be advisable for the protection of property and persons against any hazards that may be involved in the handling and use of any Cartell UK Ltd's products. Cartell UK Ltd specifically disclaims all warranties express or implied, including warranties of salability and suitability for a particular purpose arising from sale or use of Cartell UK Ltd's products. Cartell UK Ltd further disclaims any liability for consequential or incremental damages of any kind including lost profits.

Revision date: 01/2025 - Revision: 08

